## IN THE CLAIMS

Please amend the claims as follows:

- 1. (original) Method for fabrication of an electric incandescent lamp, comprising the steps of:
- coiling a first coil of a wire having diameter d around a first mandrel having diameter M1 with a first pitch and a first number of turns;
- winding said first coil around a second mandrel having diameter M2 with a second pitch and a second number of turns to form a coiled coil filament;
- arranging means for electrically and structurally mounting a filament within a light permeable envelope;
- arranging the coiled coil filament within the envelope, coupled to and supported by the means for mounting;
- hermetically sealing said envelope,
  characterized by heating the coiled coil filament above its
  recrystallization temperature within the envelope for
  recrystallization of said coiled coil.
- 2. (original) Method according to claim 1, the filament wire having diameter d, wherein the primary and secondary winding have primary and secondary mandrel-to-wire ratios Y1 and Y2, wherein:

$$Y1 = M1/d$ >= 3; and$$
  
 $Y2 = M2/(M1 + 2d) >= $3.$ 

- 3. (currently amended) Method according to claim 1 or 2, comprising the further steps of:
- annealing the first coil at a first annealing temperature after coiling thereof;
- cleaning the coiled coil filament in a wet gas;
- heat treating the coiled coil filament in a dry gas atmosphere to release stresses therein;
- removing the first mandrel by inserting the coiled coil filament in acid.
- 4. (currently amended) Method according to claim 1 or 3, wherein Y1 = M1/d > 4 and Y2 = M2/(M1+2d) > 4.
- 5. (currently amended) Method according to claim 1 or 4, wherein Y1 <= #8 and/or Y2 <= #8.
- 6. (original) Electric incandescent lamp, comprising:
- a hermetically sealed light permeable envelope;
- means for electrically and structurally mounting a filament within the envelope; and

- a coiled coil filament coupled to and supported by the means for mounting, comprising a filament wire having diameter d, wherein the primary and secondary winding have primary and secondary mandrel-wire ratios Y1 and Y2, wherein:

$$Y1 = M1/d > 4$$
; and

$$Y2 = M2/(M1 + 2d) > 4$$
,

wherein M1 is the primary mandrel diameter and M2 is the secondary mandrel diameter.

- 7. (original) Lamp according to claim 6, wherein Y1# <= 8 and/or Y2# <= 8.
- 8. (currently amended) Lamp according to claim  $6 \frac{1}{2}$ , wherein Y1 >= \$4.5 and/or Y2 >= \$4.5.
- 9. (original) Lamp according to claim 6, wherein Y1# <= 6 and/or Y2# <= 6.
- 10. (currently amended) Lamp according to any of the previous claims claim 6, wherein the envelope is filled with a gas comprising halogen.

11. (currently amended) Lamp according to any of the previous claimsclaim 1, wherein the wire is a tungsten wire.